

**Advanced Materials****Araldite<sup>®</sup> LY 3508\* / Aradur<sup>®</sup> 3486\*****TOUGHENED EPOXY RESIN**

Araldite<sup>®</sup> LY 3508 is a medium viscosity toughened epoxy resin.

<b>APPLICATIONS</b>	Industrial composites		
<b>PROPERTIES</b>	Laminating Araldite <sup>®</sup> LY 3508 has a good toughness effect combined with a low viscosity		
<b>PROCESSING</b>	<ul style="list-style-type: none"> <li>• Wet lay-up</li> <li>• Filament Winding</li> <li>• Pressure Moulding</li> <li>• Resin Transfer Moulding (RTM)</li> </ul>		
<b>PRODUCT DATA</b>	<b>Araldite<sup>®</sup> LY 3508</b>		
	Aspect (visual)	white liquid	
	Viscosity at 25 °C (ISO 2555)	11000 – 20000 **	[mPa s]
	Density at 25 °C (ISO 1675)	1.15 - 1.20	[g/cm <sup>3</sup> ]
	Epoxy value (ISO 3001)	4.8 - 5.4 **	[Eq/kg]
	<b>Aradur<sup>®</sup> 3486</b>		
	Aspect (visual)	clear colourless to slightly yellow liquid	
	Viscosity at 25 °C (ISO 12058-1)	10 - 20	[mPa s]
	Density at 25 °C (ISO 1675)	0.94 - 0,95	[g/cm <sup>3</sup> ]
	Amine value (ISO 9702)**	8.55 - 9.30	[Eq/kg]

\*\* Specified data are on a regular basis analysed. Data which is described in this document as 'typical' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

<b>STORAGE</b>	<p>Provided that Araldite<sup>®</sup> LY 3508, Aradur<sup>®</sup> 3486 are stored in a dry place in their original, properly closed containers at the storage temperatures mentioned in the MSDS they will have the shelf lives indicated on the labels. Partly emptied containers should be closed immediately after use.</p> <p>Epoxy Resin XU 3508 which has crystallized and looks cloudy can be restored to its original state by heating to 60 - 80 °C.</p>
----------------	---

*In addition to the brand name product denomination may show different appendices , which allows us to differentiate between our production sites: e.g , BD = Germany, US = United States, IN = India, CI = China, etc.. These appendices are in use on packaging, transport and invoicing documents.*

*Generally the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact.*

**TYPICAL SYSTEM DATA****PROCESSING DATA**

<b>MIX RATIO</b>	<i>Components</i>	<i>Parts by weight</i>	<i>Parts by volume</i>
	Araldite® LY 3508	100	100
	Aradur® 3486	30	37

We recommend that the components are weighed with an accurate balance to prevent mixing inaccuracies which can affect the properties of the matrix system. The components should be mixed thoroughly to ensure homogeneity. It is important that the side and the bottom of the vessel are incorporated into the mixing process.

When processing large quantities of mixture the pot life will decrease due to exothermic reaction. It is advisable to divide large mixes into several smaller containers.

<b>INITIAL MIX VISCOSITY</b> (CONE PLATE)	LY 3508 / Aradur® 3486	[°C] at 25		[mPa s] 720 - 860
<b>POT LIFE</b> (TECAM)	LY 3508 / Aradur® 3486	[°C] at 23	[g] 100	[min.] 380 – 480
<b>GEL TIME</b> (HOT PLATE)	LY 3508 / Aradur® 3486	[°C] at 100 at 120		[min] 9 – 14 3 – 7

The values shown are for small amounts of pure resin/hardener mix. In composite structures the gel time can differ significantly from the given values depending on the fibre content and the laminate thickness.

**PROPERTIES OF THE CURED, NEAT FORMULATION**

<b>GLASS TRANSITION TEMPERATURE</b> (ISO 11357-2, DSC, 10 K/MIN)	<i>Cure:</i> 16 h 50 °C 5 h 100 °C	$T_G$ [°C] [°C]	<i>LY 3508</i> <i>Aradur 3486</i> 68 – 74 95 – 102
<b>FLEXURAL TEST</b> (ISO 178)	<i>Cure:</i> 5 h 100 °C		<i>LY 3508</i> <i>Aradur 3486</i>
	Flexural strength	[MPa]	110 - 125
	Elongation at flexural strength	[%]	5.8 – 6.8
	Ultimate strength	[MPa]	90 - 1005
	Ultimate elongation	[%]	10.0 – 12.5
	Flexural modulus	[MPa]	2750 – 2950
<b>FRACTURE PROPERTIES BEND NOTCH TEST</b> (ISO 13586)	<i>Cure:</i> 1 h 80 °C + 8 h 140 °C		<i>LY 3508</i> <i>Aradur 3486</i>
	Fracture toughness $K_{1C}$	[MPa√m]	2.2 – 2.4
	Fracture energy $G_{1C}$	[J/m <sup>2</sup> ]	1500 - 1700
<b>WATER ABSORPTION</b> (ISO 62)	<i>Cure:</i> 1 h 80 °C + 8 h 140 °C  10 days H <sub>2</sub> O 23 °C		<i>LY 3508</i> <i>Aradur 3486</i>  [%] 0.48 – 0.55

**HANDLING  
PRECAUTIONS****Personal hygiene***Safety precautions at workplace*

protective clothing	yes
gloves	essential
arm protectors	recommended when skin contact likely
<u>goggles/safety glasses</u>	<u>yes</u>

*Skin protection*

before starting work	Apply barrier cream to exposed skin
<u>after washing</u>	<u>Apply barrier or nourishing cream</u>

*Cleansing of contaminated skin*

Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels.  
Do not use solvents

*Disposal of spillage*

Soak up with sawdust or cotton waste and deposit in plastic-lined bin

*Ventilation*

of workshop	Renew air 3 to 5 times an hour
of workplaces	Exhaust fans. Operatives should avoid inhaling vapours

**FIRST AID**

Contamination of the *eyes* by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the *skin* should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after *inhaling* vapours should be moved out of doors immediately.

In all cases of doubt call for medical assistance.

**Huntsman Advanced Materials**

(Switzerland) GmbH  
Klybeckstrasse 200  
4057 Basel  
Switzerland

Tel: +41 (0)61 299 11 11  
Fax: +41 (0)61 299 11 12

[www.huntsman.com/advanced\\_materials](http://www.huntsman.com/advanced_materials)  
Email: [advanced\\_materials@huntsman.com](mailto:advanced_materials@huntsman.com)



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2012 Huntsman Corporation or an affiliate thereof. All rights reserved.