ZI Haneboesch L-4562 Differdange LUXEMBOURG

Phone: +352 58 22 82 1 Fax: +352 58 49 35

E-mail: sales@airtech.lu Website: www.airtech.lu

## **Data Sheet**

# **DAHLAR® MLF 52**

# Fluorocarbon shrink tape

#### DESCRIPTION

Dahlar® MLF 52 is a modified fluorocarbon shrink tape that has high elongation, eliminating wrinkles when applying to the laminate and will release from any resin system. The tape does not have any release coating but will exhibit natural release characteristics.

## **TECHNICAL DATA**

Fluorocarbon Material type

Blue Nominal shrinkage (lengthwise) at 149 °C 20 % Maximum shrink pressure (lengthwise) 9,3 MPa Starts to shrink 32°C 93-232 °C Temperature range for practical use

Approximate time to reach full shrink after exposure

to temperature

1 minutes

Shelf life 18 months from date of shipment when stored at 22 °C

#### **SIZES**

Thickness	Width	Length
0,002 inch (50,8 μm)	0,75 inch (1,90 cm)	100 yards (91,4 m)
0,002 inch (50,8 μm)	1 inch (2,54 cm)	100 yards (91,4 m)
0,002 inch (50,8 μm)	1,25 inches (3,17 cm)	100 yards (91,4 m)
0,002 inch (50,8 μm)	2 inches (5,08 cm)	100 yards (91,4 m)
0,002 inch (50,8 µm)	2.5 inches (6.35 cm)	100 vards (91.4 m)



## **NOTES**

Other sizes available on special request.

Last updated: 2015-11-24