

Advanced Materials**Araldite® AV 4415 / Hardener HV 4416-1****Structural Adhesives****Araldite® AV 4415 / Hardener HV 4416-1****Two component epoxy paste adhesive for pipe bonding****Key properties**

- Temperature resistant up to 180 °C
- Excellent resistance to most common chemicals
- Non flowing paste for ease of application
- Gap filling
- Bonds a wide range of substrate materials
- Post cure recommended for optimum properties

Description

Araldite® AV 4415 with Hardener HV 4416-1 is a two component, ambient temperature gelling paste adhesive, which after post curing at temperatures up to 150 °C, will give bonds with temperature resistance up to 180 °C and excellent resistance to common chemicals. It is suitable for bonding a range of ferrous metals and aluminium alloy substrates and polymeric substances such as GRE, GRP, ABS and SMC.

Typical product data

Property	Araldite® AV 4415	Hardener HV 4416-1	Mixed Adhesive
Colour (visual)* (A112)	White-beige paste	Black paste	Dark grey paste
Viscosity at 25°C* (Pa.s) (A191)	120 - 240	65 - 120	thixotropic
Specific gravity	1.55 - 1.65	1.55 - 1.65	1.55 - 1.65
T _g midpoint* (2h, 150 °C) (A76)*			> 125 °C
Lap shear strength at 25 °C* (A501)*			> 16 MPa
Pot Life (100 g at 25°C)	-	-	80 - 90 minutes

* Specified data are on a regular basis analysed. Data which is described in this document as 'typical' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

Processing**Pretreatment**

The strength and durability of a bonded joint are dependent on proper treatment of the surfaces to be bonded. At the very least, joint surfaces should be cleaned with a good degreasing agent such as acetone or other proprietary degreasing agents in order to remove all traces of oil, grease and dirt. Low-grade alcohol, gasoline (petrol) or paint thinners should never be used. The strongest and most durable joints are obtained by either mechanically abrading or chemically etching ("pickling") the degreased surfaces. Abrading should be followed by a second degreasing treatment

Mix ratio	Parts by weight	Parts by volume
Araldite® AV 4415	100	100
Hardener HV 4416-1	50	50

Resin and hardener should be mixed together at room temperature stirring thoroughly.

Application of adhesive

The resin/hardener mix is applied directly or with a spatula, to the pretreated and dry joint surfaces.

A layer of adhesive 0.05 to 0.10mm thick will normally impart the greatest lap shear strength to the joint.

The joint components should be assembled and clamped as soon as the adhesive has been applied. An even contact pressure throughout the joint area will ensure optimum cure.

Mechanical processing

Specialist firms have developed metering, mixing and spreading equipment that enables the bulk processing of adhesive. We will be pleased to advise customers on the choice of equipment for their particular needs.

Equipment maintenance

All tools should be cleaned with hot water and soap before adhesives residues have had time to cure. The removal of cured residues is a difficult and time-consuming operation.

If solvents such as acetone are used for cleaning, operatives should take the appropriate precautions and, in addition, avoid skin and eye contact.

Typical cure requirements

Temperature	°C	40	60	100
Cure time to reach Lap shear strength > 1 MPa		80 min.	15 min.	< 5
Cure time to reach Lap shear strength > 10 MPa		6 h	40 min.	15 min.

To achieve optimum performance properties an elevated temperature cure or post cure is recommended. Lap shear strength of 1 MPa represents a strength where careful handling of the bonded object is possible. This adhesive will not fully cure at temperatures below 60°C.

Suggested cure schedules are:

8hrs at 80°C or 1 hr at 130°C or 30 mins at 150°C

Typical cured properties


Unless otherwise stated, the figures given below were all determined by testing standard specimens made by lap-jointing 114 x 25 x 1.6 mm strips of aluminium alloy. The joint area was 12.5 x 25 mm in each case.

The figures were determined with typical production batches using standard testing methods. They are provided solely as technical information and do not constitute a product specification.

Average lap shear strengths of typical metal-to-metal joints (ISO 4587) (typical average values)

Cured for 24 hours at 23°C + 1 hour at 130°C and tested at 23°C


Pretreatment - Sand blasting



Average lap shear strengths of typical plastic-to-plastic joints (ISO 4587) (typical average values)


Cured for 24 hours at 23°C + 1 hour at 130°C and tested at 23°C

Pretreatment - Lightly abrade and alcohol degrease.



Lap shear strength versus temperature (ISO 4587) (typical average values)


Cure: = 24 hours at 23°C + 1 hour at 130°C



Lap shear strength versus immersion in various media (typical average values)

Unless otherwise stated, L.S.S. was determined after immersion for 90 days at 23°C


Cure: 24 hours at 23°C + 1 hour at 130°C



Lap shear strength versus tropical weathering (typical average values)

40°C / 92% Relative Humidity

Cure: 24 hours at 23°C + 1 hour at 130°C and tested at 23°C

**DMA measurement (typical average values)**

Cure: 24 hours at 23°C + 1 hour at 130°C

100°C 1.3 GPa

125°C 0.5 GPa

150°C 39 MPa

175°C 39 MPa

200°C 43 MPa

Glass transition temperature (T_g) 135°C

Storage

Araldite® AV 4415 with HV 4416-1 hardener may be stored at room temperature, provided storage is in original sealed containers. The expiry date is indicated on the label.

**Handling
Precautions****Caution**

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with food-stuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.



Huntsman Advanced Materials
(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.aralditeadhesives.com

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, **nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.**

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2017 Huntsman Corporation or an affiliate thereof. All rights reserved