



Version: TE027/02

Tectyl™ 400-C

Premium solvent based corrosion preventive compound

Tectyl 400-C is a solvent cutback, wax base, corrosion preventive compound.

Tectyl 400-C is designed to protect metal surfaces against corrosion in long-term indoor or short-term outdoor exposure and during domestic and overseas shipment.

Tectyl 400-C cures to a dark amber colored, waxy, transparent, firm film.

Approvals/Performance levels

Tectyl 400-C

Accelerated Corrosion tests:
@ Average recommended DFT

Accelerated Corrosion tests:
Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS
(Q-Panels, Type R, ASTM A1008)

At least 8 days

Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH
(Q-Panels, Type R, ASTM A1008)

At least 21 days

Estimated Protection Period

Indoor: 24 months
Outdoor: 6 months

Applications

Surface preparation

The maximum performance of Tectyl 400-C can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. CorPro recommends that the metal substrate temperature is 10-35 °C at the time of product application.

Application

Tectyl 400-C is formulated to be used as supplied. CorPro recommends that the ambient and product temperature be 10-35 °C at the time of product application. Always ensure uniform consistency prior to use. Continued stirring is generally not required. If the product thickens due to cold storage or loss of solvent during use, contact CorPro. Do not thin Tectyl 400-C. Incorrect thinning will affect film build, dry time and product performance. Tectyl 400-C can be applied by low pressure air spray or dipping. Details on application can be found in the application chart.

Removal

Tectyl 400-C can in the wet phase be removed with low-pressure steam.

Features & Benefits

Excellent protection

Tectyl 400-C protects your parts during storage, domestic and overseas transport against corrosion.

Economical solution

With the thin layer of only 25 microns a large area can be protected against corrosion.

Easy application

Tectyl 400-C can be applied by low pressure air spray, but also by dipping the parts in a bath filled with Tectyl 400-C.



Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit www.tectyleurope.com

Typical properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl 400-C	
Flash Point, PMCC [°C]	40
Density @ 20°C [kg/ltr]	0.86
Recommended Dry Film Thickness over metal profile [microns]	25
Theoretical coverage @ recommended DFT [m²/ltr]	16.3
Non Volatile [weight %]	47
Viscosity; DIN (53211) Cup No. 4 @ 20°C (at time of manufacture) [sec]	23
Dry to touch time @ 20°C [hours]	1
Cure time @ 20°C [hours]	24
Volatile Organic Compound Content ISO 11890-2 (10.4) [g/ltr]	471

This information only applies to products manufactured in the following location(s): Europe

Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office.

Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.

Storage

Tectyl 400-C should be stored at temperatures between 10-35 °C. Do not freeze Tectyl 400-c. Mild agitation is recommended prior to use. Due to its composition Tectyl 400-C can be subject to postproduction viscosity changes during storage. Under proper storage conditions Tectyl 400-C is best before 36 months after production date.

Caution

Adequate ventilation is required for cure and to ensure against formation of combustible liquid. The partially cured film should not be exposed to ignition sources such as flares, flames, sparks, excessive heat or torches. Refer to the Safety Data Sheet for additional handling and first aid information.

Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Performance level section. If a primer, other than a CorPro recommended product is required, written authorization must be obtained from CorPro.

Replaces – TE027/01

™ Trademark of CorPro, registered in various countries © 2022