

## SPG Special Plastics Grease

Page 1

SPG is a synthetic grease offering outstanding low temperature performance and excellent compatibility with thermoplastics, including ABS and Polycarbonate, even at elevated temperatures. SPG is an efficient mechanical lubricant for plastics both with themselves and with metals. A harder, more adhesive version of SPG is available called SPGA.

- Excellent plastics compatibility; suitable for use with sensitive plastics (testing advised)
- Tacky characteristic; high tenacity to stay in contact zone
- Stays where placed even on vertical surfaces; ideal for plastic-plastic lubrication
- Excellent at holding components in place during assembly

### Approvals

**RoHS Compliant (2015/863/EU):**
**Yes**

### Typical Properties

Colour	Light Brown
Density (g/ml)	0.9
Temperature Range (°C)	-40 to +125
Evaporation Weight Loss (% 7 days @ 100°C)	0.6
Evaporation Weight Loss (% 7 days @ 125°C)	0.6
Copper Strip Corrosion (IP154 / ISO 2160)	≤1b
Drop Point (IP32 / ISO 2176 (°C))	>250
Cone Penetration Worked (ASTM D217, 60 strokes @ 20°C)	320
Cone Penetration Un-worked (ASTM D 217 @ 20°C)	300
Cone Penetration Un-worked (ASTM D 217 @ -40°C)	220
Consistency (NLGI)	1
Fließdruck (Flow Pressure) (DIN 51805, mbar @ -40°C)	450
Oil Bleed / Separation (IP121)	5%
Plastic Compatibility - ABS	Test
Plastic Compatibility - PC	Test
Thickener	Clay
UV Trace	No

#### Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,  
Ashby de la Zouch,  
Leicestershire LE65 1JR

T +44 (0)1530 419 600

F +44 (0)1530 416 640

BS EN ISO 9001:2008  
Certificate No. FM 32082

**Base Oil Properties**

Base Oil Type	PAO
Base Oil Viscosity @ 40°C (Kinematic Viscosity (cSt))	46
Base Oil Viscosity @ 100°C (Kinematic Viscosity (cSt))	7.8
Base Oil Viscosity Index (ASTM D 2270)	139
Pour Point (ASTM D 97 (°C))	-57
Flash Point (COC ASTM D 92 (°C))	>200

**Mechanical Properties:**

4 Ball Wear (mm)	2.508
Weld Load (kgf)	126

<b><u>Packing</u></b>	<b><u>Order Code</u></b>	<b><u>Shelf Life</u></b>	<b><u>Container Dimension</u></b>
900g Bulk	SPG900G	72 Months	
10Kg Bulk	SPG10K	72 Months	300mm (Diameter) x 285mm (Height)
20Kg Bulk	SPG20K	72 Months	300mm (Diameter) x 445mm (Height)
52Kg Bulk	SPG52K	72 Months	
170Kg Bulk	SPG200L	72 Months	
35ml Syringe	SPG35SL	48 Months	

**Directions for Use**

Depending on packaging type, this lubricant can be applied by one of the following methods (although this list is not exhaustive):

**Manually** by way of a syringe

**Semi-automated** using syringe dispensing

**Fully automated** by way of a follower/pusher plate with dispensing system

**Typical Product Applications**

SPG has been formulated to ensure compatibility with plastics and metals commonly used in the manufacture of electrical switches. It is particularly recommended as an assembly aid in switch manufacture (montage grease). It is also ideal to reduce wear in timers and other plastic/plastic friction points (e.g. photocopiers).

Revision 3: Jan 2019

**Copyright Electrolube 2013**

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way,  
Ashby de la Zouch,  
Leicestershire LE65 1JR

T +44 (0)1530 419 600

F +44 (0)1530 416 640

BS EN ISO 9001:2008  
Certificate No. FM 32082