

**Advanced Materials****Araldite® LY 3585 / Aradur® 22962**

Araldite® LY 3585 is an epoxy resin  
 Aradur® 22962 is a cycloaliphatic polyamine

<b>APPLICATIONS</b>	Industrial composites		
<b>PROPERTIES</b>	Reactive diluent free laminating system. Due to the high reactivity, short cure cycles can be realized.		
<b>PROCESSING</b>	<ul style="list-style-type: none"> <li>• Wet lay-up</li> <li>• Pressure Moulding</li> <li>• Resin Transfer Moulding (RTM)</li> </ul>		
<b>KEY DATA</b>	<b>Araldite® LY 3585</b>		
	Aspect (visual)	clear liquid	
	Viscosity at 25 °C (ISO 12058-1)	6500-8000	[mPa s]
	Density at 25 °C (ISO 1675)	1.15 - 1.20	[g/cm <sup>3</sup> ]
	Flash point (ISO 2719)	> 200	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
	<b>Aradur® 22962</b>		
	Aspect (visual)	clear liquid	
	Viscosity at 25 °C (ISO 12058-1)	5 - 20	[mPa s]
	Density at 25 °C (ISO 1675)	0.89 - 0.90	[g/cm <sup>3</sup> ]
	Flash point (ISO 2719)	≥ 110	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
<b>STORAGE</b>	Provided that Araldite® LY 3585 and Aradur® 22962 are stored in a dry place in their original, properly closed containers at the above mentioned storage temperatures they will have the shelf lives indicated on the labels. Partly emptied containers should be closed immediately after use.		

**PROCESSING DATA**

<b>MIX RATIO</b>	<i>Components</i>	<i>Parts by weight</i>	<i>Parts by volume</i>
	Araldite® LY 3585	100	100
	Aradur® 22962	24	32

We recommend that the components are weighed with an accurate balance to prevent mixing inaccuracies which can affect the properties of the matrix system. The components should be mixed thoroughly to ensure homogeneity. It is important that the side and the bottom of the vessel are incorporated into the mixing process. When processing large quantities of mixture the pot life will decrease due to exothermic reaction. It is advisable to divide large mixes into several smaller containers.

<b>INITIAL MIX VISCOSITY</b>	<i>[°C]</i>	<i>[mPa s]</i>
(HAAKE VT 500, DIN 53 019)	at 40	220 - 260

<b>VISCOSITY BUILD-UP</b>	<i>[°C]</i>	<i>[mPa s]</i>	<i>[min]</i>
(HAAKE VT 500, DIN 53 019)	at 40	to 500 to 1500	12 - 16 31 - 35

<b>POT LIFE</b>	<i>[°C]</i>	<i>[min]</i>
(TECAM, 100 ML, 65 % RH)	at 23	110 - 125

<b>GEL TIME</b>	<i>[°C]</i>	<i>[min]</i>
(HOT PLATE)	at 80	16 - 20
	at 100	8 - 11
	at 120	3 - 5

The values shown are for small amounts of pure resin/hardener mix. In composite structures the gel time can differ significantly from the given values depending on the fibre content and the laminate thickness.

<b>TYPICAL CURE CYCLES</b>	30 min 120 °C or 15 min 120 °C + 2 h 150 °C
----------------------------	--

The optimum cure cycle has to be determined case by case depending on the processing and the economic requirements.

**PROPERTIES OF THE CURED, NEAT FORMULATION**

<b>GLASS TRANSITION TEMPERATURE</b> (IEC 1006, DSC, 10 K/MIN)	<i>Cure:</i> 30 min 120 °C 15 min 120 °C + 2 h 150 °C	<i>T<sub>G</sub> [°C]</i> 120-130 150-160
--	---	---

<b>FLEXURAL TEST</b> (ISO 178)	<i>Cure:</i> 15 min 120 °C + 2 h 150 °C		
	Flexural strength	[MPa]	130-140
	Ultimate elongation	[%]	7.5-9
	Flexural modulus	[MPa]	2750 – 2950

<b>FRACTURE PROPERTIES</b> <b>BEND NOTCH TEST</b> (PM 258-0/90)	<i>Cure:</i> 15 min 120 °C + 2 h 150 °C		
	Fracture toughness K <sub>1C</sub>	[MPa√m]	0.65 - 0.75
	Fracture energy G <sub>1C</sub>	[J/m <sup>2</sup> ]	130 – 160

**PROPERTIES OF THE CURED, REINFORCED FORMULATION**

<b>INTERLAMINAR SHEAR STRENGTH</b> (ASTM D 2344)	Samples: 12 layers E-glass fabrics UD (425 g/m <sup>2</sup> ) Laminate thickness = 3.1 - 3.25 mm Fibre volume content: 59 - 63 % Cure: 15 min 120 °C + 2 h 150 °C		
	Shear strength	[MPa]	63 -69

---

**HANDLING  
PRECAUTIONS****Personal hygiene**

---

*Safety precautions at workplace*

protective clothing	yes
gloves	essential
arm protectors	recommended when skin contact likely
goggles/safety glasses	yes

---

*Skin protection*

before starting work	Apply barrier cream to exposed skin
after washing	Apply barrier or nourishing cream

---

*Cleansing of contaminated skin*

Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels.  
Do not use solvents

---

*Disposal of spillage*

Soak up with sawdust or cotton waste and deposit in plastic-lined bin

---

*Ventilation*

of workshop	Renew air 3 to 5 times an hour
of workplaces	Exhaust fans. Operatives should avoid inhaling vapours

---

**FIRST AID**

Contamination of the *eyes* by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the *skin* should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after *inhaling* vapours should be moved out of doors immediately. In all cases of doubt call for medical assistance.

**IMPORTANT LEGAL NOTICE**

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Aradur and Araldite are registered trademarks of Huntsman Corporation or an affiliate thereof.

Copyright © 2011 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Office :  
**Huntsman Advanced Materials (Switzerland) GmbH**  
Klybeckstrasse 200  
4057 BASEL  
Switzerland  
+41 61 299 1111