

LC 177

**ELASTIC, THERMAL AND IMPACT RESISTANT,
MONO COMPONENT UV-CURABLE ACRYLATE**

TECHNICAL DATA SHEET

June 2022



PRODUCT DESCRIPTION

Bostik Born2Bond™ LC range is based on a patented UV acrylic adhesives technology and shows unmatched performance in term of resistance and flexibility.

These adhesives are transparent and have been designed for bonding a wide range of dissimilar substrates for industrial applications, including metals if bonded to a transparent material. The outstanding properties of Bostik LC range allow structural bonding while keeping flexibility.

The Bostik LC range products has been developed to resist aggressive environments. It shows unprecedented results facing weathering and ageing.

KEY FEATURES

1. UV curing
2. Temperature resistance
3. Impact resistance
4. Excellent environmental resistance
5. Elastic behavior
6. Low water absorption
7. Gap filling up to 2 mm

DIRECTIONS FOR USE

Before applying LC177 make sure the surface is clean, dry and grease-free. Most plastics require a simple cleaning before bonding. Some may require surface treatment for better performances. The optimum qualities are obtained at room temperature, between 12° C and 35° C without post-curing. Avoid contact with direct sun light or any other artificial light source. Materials must be stored in cool place away from sources of heat. Read material Safety Data Sheet before handling or using this product.

Curing time must be determined and qualified in real conditions and environment of the intended use, as it will vary depending on parameters such as substrate light absorption, adhesive thickness, light spectrum, irradiation intensity, distance from the lamp, temperature. For process robustness, Bostik advises to increase light exposure time and/or light intensity used during the initial curing time qualification, in order to absorb all possible variations of the operational conditions.

METHOD OF USE

Manual: Directly from the syringe with or without dispensing cannula for more precise dispensing.

Semi-Automated: Use of pressure-time systems for accurate volume and larger series.

Full-Automated: fully automated robot or application lines (progressive cavity pumps or screw pumps).

APPLICATIONS

Typical applications for this product are fast bonding of metal, plastic and glass parts.

STORAGE/SHELF LIFE

The LC177 shelf life is 6 months in unopened original packaging. The product may be stored in a closed container in a dry place at temperature between 5° C and 25° C. Exposure to higher or lower temperature will result in a reduction of the stated shelf life.

HEALTH/SAFETY

The Safety Data Sheet is available on the Bostik website and should be consulted for proper handling, cleanup and spill containment before use. Keep containers covered to minimize contamination.

LIMITATIONS

This product is not recommended for use in pure oxygen and/or oxygen-rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. Material removed from containers may be contaminated during use. Do not return product to the original container. Bostik will not assume responsibility for product that has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or customer service representative.

PRODUCT CHARACTERISTICS

Basis Technology	UV-Acrylate
Components	1K
Appearance/Color	Transparent
Cure	LED (365nm, 385nm, 405 nm) UVA

UNCURED PHYSICAL PROPERTIES

Viscosity (mPa.s) -2 rpm	110.000-150.000
Density	1,02-1,05
Appearance/Color Liquid	Clear/yellowish

FIXTURE TIME

Test on glass (gap: 0,125 mm)

UVA Intensity 50-60 mW/cm ²	7 ± 0,5 s
---	-----------

LED 405 nm Intensity 2 W/cm ²	4 ± 0,5 s
---	-----------

CURING PHYSICAL PROPERTIES

Shore Hardness D (ISO 868)	20-35
Tensile Strength (ISO 527)	9-11 MPa
Nominal Elongation at Break (ISO 527)	200-230%
Tg (DMA)	49°C
Water absorption after 48 h (ASTM D542)	≤ 1 %
Volume Shrinkage (ISO 10563)	8 ± 0,5 %

SUBSTRATES RECOMMENDATION

Substrates	Recommendation
ABS	X
PA	O
PMMA	X
PBT	O
PC	O
SAN	X
Glass	X
Aluminium	X
Stainless Steel	X

X: Recommended

O : Limited application

BONDING PERFORMANCE


Lapshear strength (ISO 4587) @ 23° C (MPa)

Samples were prepared using UVA lamp with an irradiation measured on sample of 40-50 mW/cm² for 60 s and a gap of 0,25 mm.

PMMA/ABS	7 ± 1
PMMA/PMMA	7 ± 1
SAN/SAN	7 ± 1
Glass/Glass	5 ± 1
PMMA/Aluminum	6 ± 1
PMMA/Stainless Steel	8 ± 1

HEAT AGING


Lapshear strength (ISO 4587) @ 23° C after aging at 80°C. Samples were prepared using UVA lamp with an irradiation measured on sample of 40-50 mW/cm² for 60 s and a gap of 0,25 mm. Adhesive was applied between two glass plates.



HEAT/HUMIDITY AGING

Lapshear strength (ISO 4587) @ 23°C after aging under humid conditions.

Samples were prepared using UVA lamp with an irradiation measured on sample of 40-50 mW/cm² for 60 s and a gap of 0,25 mm. Adhesive was applied between two PMMA plates. and aged at 95%RH, 40°C.



CYCLE AGING

Lapshear strength (ISO 4587) @ 23° C after cycle ageing.

Samples were prepared using UVA lamp with an irradiation measured on sample of 40-50 mW/cm² for 60 s and a gap of 0,25 mm. Samples were submitted to a 24h heat and temperature cycle splitted in 3 phases (plus ramp-up times) :

- i. 15h at 40° C, RH > 90%
- ii. 2h at -20° C
- iii. 4h at 70° C, 50 % RH

Results after 7 cycles

Substrates	% of Initial Strength
PMMA/PMMA	67
PMMA/Alu	150
PMMA/ABS	90

LIGHT AGING

Lapshear strength (ISO 4587) @ 23° C after UVA exposure Samples were prepared using UVA lamp with an irradiation measured on sample of 40-50 mW/cm² for 60 s and a gap of 0,25 mm.

Results after 1000h

Substrates	% of Initial Strength
PMMA/PMMA	50 (no yellowing)

PRODUCT DISCLAIMER

Bostik offers this Technical Data Sheet (“TDS”) for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided ‘AS IS’ and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik’s research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. **BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BOSTIK’S PRODUCTS.**

The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for application, among other things. Any change in any of these variables can affect the product’s performance.

You are responsible to test the suitability of any product in advance for any intended use or application. Bostik does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS. Nothing contained herein constitutes a license to practice under any patent, and it should not be construed as an inducement to infringe any patent. You are advised to take appropriate steps to be sure that any proposed use of the products will not result in patent infringement.

The information provided herein relates only to the specific products designated and may not be applicable when such products are used in combination with other materials or in any process. The product is sold pursuant to a supply agreement and/or Bostik’s Terms and Conditions of Sale, which set forth the sole warranty, if any, that applies to the product. **NO OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE OR WARRANTY OF MERCHANTABILITY, IS MADE CONCERNING THE PRODUCTS DESCRIBED OR THE INFORMATION PROVIDED HEREIN, AND TO THE MAXIMUM EXTENT ALLOWED BY LAW, SUCH WARRANTIES ARE HEREBY DISCLAIMED. BOSTIK DISCLAIMS ANY LIABILITY FOR DIRECT, INCIDENTAL, CONSEQUENTIAL, OR SPECIAL DAMAGES TO THE MAXIMUM EXTENT ALLOWED BY LAW.**