



Features & Benefits

-  Ultra-low viscosity
-  For fingerprinting

Description

PERMABOND CPP621 is a special cyanoacrylate which has been formulated to give maximum vapour evolution when used in conjunction with the fingerprint cabinet as specified by the Home Office (or similar). The product gives more fuming and less residue on heating than regular cyanoacrylates, offering the user potential cost savings.

Physical Properties of Uncured Adhesive

| | |
|----------------------|---------------------|
| Chemical composition | Ethyl cyanoacrylate |
| Appearance | Colourless |
| Viscosity @ 25°C | 1-3 mPa.s (cP) |
| Specific gravity | 1.05 |

Instructions for Use

1. Place item to be fingerprinted into suitable fuming chamber.
2. Optimal fuming conditions are 80% relative humidity which can be achieved with a 120°C hotplate gently heating a dish of water.
3. Add a separate dish containing the Permabond CPP621 at a quantity specific to the volume of the chamber (for example 1g in a 200 litre volume chamber).
4. Make sure the chamber is fully sealed.
5. Development time is 5 to 30 minutes (normally around 20 minutes in a 200 litre chamber).
6. Remove item. A white residue should be visible – this can then be transferred for further processing as desired.

Storage & Handling

| | |
|--|-----------|
| Storage Temperature | 2 to 7°C |
| Shelf Life Stored in original unopened containers | 12 months |

Allow adhesive to reach room temperature before opening bottle to prevent condensation inside the bottle which can reduce shelf life.

This Technical Datasheet (TDS) offers guideline information and does not constitute a specification.

www.permabond.com

• UK: 0800 975 9800

• General Enquiries: +44 (0)1962 711661

• US: 732-868-1372

• Asia: + 86 21 5773 4913

info.europe@permabond.com

info.americas@permabond.com

info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.