

## Merbenit MB55

**Merbenit MB55 is an elastic adhesive with high strength. Adheres thanks SMP base to various materials and surfaces. Particularly resistant against environmental influences; fulfils the requirements of the International Maritime Organisation IMO.**

### Product advantages

- Simple processing
- Compatible with paints
- Wide adhesion range
- Permanently elastic, good mechanical strength
- Adjustable
- Odourless
- Chemical neutral polymerisation
- Impact and vibration resistant (shock absorbing)
- Very good sealing properties
- Shortly resistant up to +200°C for powder and thermal coating
- Tolerance compensating

### Technical data

|                                          |                                 |
|------------------------------------------|---------------------------------|
| Chemical base                            | Silane modified polymer         |
| Mechanism of curing                      | 1 comp. moisture curing         |
| Shore A hardness, DIN 53505              | 55                              |
| Modulus elongation at 100%, DIN 53504 S2 | ca. 1.3 N/mm <sup>2</sup>       |
| Elongation at break, DIN 53504 S2        | ca. 300%                        |
| Tensile strength, DIN 53504 S2           | ca. 2.1 N/mm <sup>2</sup>       |
| Consistency                              | stable                          |
| Tooling time                             | max. 10 min.                    |
| Curing rate after 24h                    | ≥ 2.0 mm                        |
| Curing rate after 48h                    | ≥ 4.0 mm                        |
| Density                                  | 1.53 +/- 0.05 g/cm <sup>3</sup> |
| Volume change, DIN EN ISO 10563          | ≤ 6%                            |
| Temperature resistance after curing      | - 40 °C to + 90 °C              |
| Application temperature                  | + 5 °C to + 40 °C               |

All measurements were performed under normal conditions (23 °C and 50 % relative humidity).

The data are based on the results after 3 months.

### Application

Flexible bonding of hatches, skirting boards, winches, plates, tubes braces, profiles, stiffenings, fixtures, fittings, deck fittings, frames, floor plates, boxes, booths, panels, sandwich panels, lightweight panels, containers, trailers, floor tiles, covers, bezels, cuffs and edge protection. Areas: shipbuilding, metal, equipment, machinery, electrical, plastics, car body, wagon, vehicle and container. Avoid contact points to non-system adhesives and sealants of other manufacturers.

### Substrate range

Suitable materials are metals, powder-coated, varnished, galvanised, anodised, chromed or hot zinc dipped surfaces, various plastics, ceramics, stone, concrete and wood. Due to the large variety of different plastics and compositions as well as materials which are susceptible to cracks, preliminary tests are recommended.

### Meets the standards

- IMO FTPC Parts 2+5

# Technical data sheet Merbenit MB55

## Substrate preparation

To achieve reproducible results the substrate has to be pre-treated according to the state of technology. For application the surface has to be clean, durable and free of dust, oil and grease. All undefined surfaces must be removed using suitable methods. Apply the adhesive/sealant promptly to the prepared surface. Depending on the substrate and the expected requirements a mechanical or chemical pre-treatment is recommended respectively cleaning with rubbing alcohol, isopropyl or acetone. The compatibility with adjacent materials, coatings etc. must be determined in advance.

## Adhesion promoter

With most materials a good adhesion is achieved even without adhesion promoter. In the case of high moisture influence we recommend our Adhesion Promoter V40 on non-porous materials, Adhesion Promoter V21 on open porous materials. For thermo-painted or powder-coated surfaces and plastic materials we recommend our Adhesion Promoter V40. Preliminary tests are recommended. Note: Adhesion promoter and thinly elapsed sealant leave stains that can not be completely cleaned.

## Processing

- Can be applied directly from the cartridge / bag using a suitable caulking gun (manual, air, battery)
- Cut the nozzle tip according to the joint width
- V-nozzles are recommended for bonding applications
- Depending on the bonding surface, material expansion, tension and mechanical stresses a layer thickness of 1 - 6 mm is recommended
- Can be applied with automatic dispensing equipment
- For vapour permeable substrates the material can be applied in a large area using a notched trowel
- The bonding must take place within the processing time
- Non-cured adhesive can be removed with rubbing alcohol or isopropyl
- Cured adhesive can only be removed mechanically

## Paint compatibility

Due to the diversity of varnishes and paints on the market we recommend preliminary tests. Using paints based on alkyd resins may delay the drying process. After cleaning with acetone joints can be varnished at any time. For burning process the material can be exposed, when fully cured, in short term to elevated temperatures.

## Chemical resistance

- Good against water, aliphatic solvents, oils, grease, diluted inorganic acids and alkalis
- Moderate against esters, ketone and aromatics
- Not resistant against concentrated acids and chlorinated hydrocarbons
- Weatherproof and resistant to aging

## Colours

- black
- grey
- white
- other colours on request

## Packaging

- Cartridges of 290 ml in boxes of 12 units
- Sausages of 600 ml in boxes of 12 units

## Shelf life and storage conditions

- 18 months from date of production
- Store cool and dry (10 - 25 °C)
- Further information on request

## Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.

**merz+benteli ag**

Freiburgstrasse 616  
CH - 3172 Niederwangen  
Phone +41 31 980 48 48  
Fax +41 31 980 48 49  
info@merz-benteli.ch  
www.merz-benteli.ch

Our information is based on experiences in lab and practice. Their publication occurs, however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne

